


Speeds and Feeds




Chipbreakers




HAL

For cost-effective machining of aluminum, non-ferrous metals, and plastics. Extremely sharp cutting edges result in optimum part finishes with low cutting forces and short chips.




HFF

For finish turning operations, producing smooth, accurate surfaces. Very good chip control, especially at low depths of cut.




HFP

For finish to medium turning operations, with optimal chip control over a wide range of cutting conditions and workpiece materials.




HFS

For finish turning operations. Ground periphery with positive cutting edge ideally suited for high-temp alloys. Micro-finished edge on the ground periphery adds just a slight hone for improved edge integrity and reliability.




HMA

For finish to rough turning operations. Flat-top geometry for machining cast iron.




HML

For finish to medium turning operations, with a negative, stable cutting edge.




HMP

For medium to rough turning operations, with reduced cutting forces and improved chip control for high feed rates. Suitable for high metal removal rates and spindling applications.



HMR

For light to medium rough-turning operations. Excellent choice for steels, difficult-to-machine high-alloy titanium, and aluminum materials. High strength to deal with heavy chip deformation.





HMS

For medium turning operations. Primarily used with high-temp materials. Utilizes a micro-finished edge preparation to increase edge toughness.

Speeds and Feeds




Chipbreakers





HMU

For medium turning operations. Medium universal geometry with a soft cutting action due to its positive profile. Versatile application range well suited for boring operations and turning unstable components.




HRH

For medium to rough turning operations. Outstanding chip control. High edge strength for interrupted cuts, forging skin, or scale. Preferred for all cast iron, such as gray, malleable, and nodular.




HUF

For finish turning operations, with a positive cutting edge for reduced cutting forces and superior surface quality.




HUM

For medium turning operations, with a soft-cutting chipbreaker. Used in applications producing varying chip sections, such as profile or copy turning. Good dimensional accuracy. For soft steel materials and stainless steels.




HUR

For rough turning operations. Improved chip forming and coolant flow for increased tool life. Positive geometry reduces cutting forces and improves depth-of-cut notching resistance. Suitable for stainless steel and smooth machining of steel.





HM

For medium turning operations. Excellent chip control in various conditions for increased productivity. Variable land reduces cutting loads at high speeds and feeds, promoting stable tool life.



AL

For finish to medium turning operations. High rake angle and a low resistance cutting edge for extended tool life in continuous cutting of aluminum, non-ferrous metals, and plastics.



HSF

For finish hard turning operations. Excellent chip control with a unique anti-vibration tip structure. Good dimensional accuracy. Excels at cutting high-hardness materials between 40-62 HRC.

Grades

Speed - m/min (ft/min) Starting Conditions

Material Group	Grade	135 (450)	180 (600)	225 (800)	275 (900)	320 (1050)	360 (1200)	410 (1350)	455 (1500)	495 (1650)	m/min	ft/min	
P0/P1	HTP15			⊕								395	1295
	HTP25		⊕									275	900
	HTM15			⊕								350	1150
	HTM25	⊕										210	690
	HTK10			⊕							330	1085	
	HTK20		⊕							285	935		
	HTS10		⊕							280	920		
	HTS25		⊕									225	740
	HTS35	⊕										210	690

Speed - m/min (ft/min) Starting Conditions

Material Group	Grade	135 (450)	180 (600)	225 (800)	275 (900)	320 (1050)	360 (1200)	410 (1350)	455 (1500)	495 (1650)	m/min	ft/min
P2	HTP15			⊕							265	870
	HTP25		⊕								195	640
	HTM15			⊕						265	870	
	HTM25	⊕									210	690
	HTK10		⊕							240	785	
	HTK20		⊕								205	675
	HTS10		⊕								200	655
	HTS25		⊕								170	560
	HTS35	⊕									150	490

Speed - m/min (ft/min) Starting Conditions [illegible]Speed - m/min (ft/min) Starting Conditions [illegible]Speed - m/min (ft/min) Starting Conditions

Material Group	Grade	120 (400)	150 (500)	180 (600)	210 (700)	240 (800)	270 (900)	300 (1000)	330 (1100)	360 (1200)	m/min	ft/min		
P5	HTP15			⊕								215	705	
	HTP25		⊕									195	640	
	HTM15			⊕									195	640
	HTM25	⊕										135	445	
	HTK10			⊕							220	720		
	HTK20		⊕									200	655	
	HTS10		⊕									200	655	
	HTS25	⊕										150	490	
	HTS35	⊕										135	445	

Speed - m/min (ft/min) Starting Conditions

Material Group	Grade	105 (350)	135 (450)	165 (550)	195 (650)	225 (750)	255 (850)	285 (950)	315 (1050)	345 (1150)	m/min	ft/min	
P6	HTP15		⊕									180	590
	HTP25		⊕								150	490	
	HTM15		⊕								160	525	
	HTM25	⊕										115	375
	HTK10		⊕									190	625
	HTK20		⊕								155	510	
	HTS10		⊕								150	490	
	HTS25		⊕									125	410
	HTS35	⊕										105	345

Speeds and Feeds



Grades

Austenitic Stainless Steel (180 HB)											Speed - m/min (ft/min) Starting Conditions ⊕	
Material Group	Grade	90 (300)	135 (450)	180 (600)	225 (800)	270 (900)	315 (1050)	360 (1200)	405 (1350)	450 (1500)	m/min	ft/min
M1	HTM15		⊕								180	590
	HTM25		⊕								150	490
	HTS10			⊕							215	705
	HTS25		⊕								180	590
	HTS35		⊕								120	395
	HTSU10		⊕								140	460

Ferritic/Martensitic Stainless Steel Mixture (Duplex) (200 HB)											Speed - m/min (ft/min) Starting Conditions ⊕	
Material Group	Grade	90 (300)	135 (450)	180 (600)	225 (800)	270 (900)	315 (1050)	360 (1200)	405 (1350)	450 (1500)	m/min	ft/min
M2	HTM15		⊕								165	540
	HTM25		⊕								140	460
	HTS10			⊕							200	655
	HTS25		⊕								165	540
	HTS35		⊕								105	345
	HTSU10		⊕								130	425
	HTH05		⊕								100	325

Martensitic Stainless Steel (240 HB)											Speed - m/min (ft/min) Starting Conditions ⊕	
Material Group	Grade	90 (300)	135 (450)	180 (600)	225 (800)	270 (900)	315 (1050)	360 (1200)	405 (1350)	450 (1500)	m/min	ft/min
M3	HTM15		⊕								150	490
	HTM25		⊕								120	395
	HTS10			⊕							185	605
	HTS25		⊕								150	490
	HTS35		⊕								90	295
	HTSU10		⊕								120	395
	HTH05		⊕								100	325

Grey Cast Iron								Speed - m/min (ft/min)				Starting Conditions		⊕
Material Group	Grade	60 (200)	180 (600)	305 (1000)	430 (1400)	550 (1800)	675 (2200)	800 (2600)	920 (3000)	1040 (3400)	1160 (3800)	m/min	ft/min	
K1	HTP15		⊕									285	935	
	HTP25		⊕									255	835	
	HTK10			⊕									450	1475
	HTK20			⊕									300	985
	HTS25		⊕							180	590			

Ductile, Compacted Graphite, and Malleable Cast Irons (<600 MPa)										Speed - m/min (ft/min)		Starting Conditions		⊕
Material Group	Grade	90 (300)	135 (450)	180 (600)	225 (750)	275 (900)	320 (1050)	360 (1200)	410 (1350)	460 (1500)	500 (1650)	m/min	ft/min	
K2	HTP15				⊕							215	705	
	HTP25				⊕							190	625	
	HTK10					⊕							360	1180
	HTK20			⊕							240	785		
	HTS10		⊕									200	655	
	HTS25		⊕									160	525	

Ductile, Malleable, and Austempered Cast Irons (>600 MPa)										Speed - m/min (ft/min)		Starting Conditions		⊕
Material Group	Grade	90 (300)	135 (450)	180 (600)	225 (750)	275 (900)	320 (1050)	360 (1200)	410 (1350)	460 (1500)	500 (1650)	m/min	ft/min	
K3	HTP15		⊕										190	625
	HTP25		⊕									170	560	
	HTK10		⊕									240	785	
	HTK20		⊕								210	690		
	HTS10		⊕								150	490		
	HTS25		⊕								135	445		
	HTH05	⊕									100	325		

Wrought Aluminum					Speed - m/min (ft/min)		Starting Conditions		⊕
Material Group	Grade	250 (800)	500 (1600)	750 (2400)	1000 (3200)	m/min		ft/min	
N1	HTSU10	⊕					490		1605

Low-Silicon Aluminum Alloys and Magnesium Alloys (Si<12.2%)					Speed - m/min (ft/min)		Starting Conditions		⊕
Material Group	Grade	250 (800)	500 (1600)	750 (2400)	1000 (3200)	m/min		ft/min	
N2	HTSU10	⊕					490	1605	

Copper-, Brass-, Zinc-Based on a Machinability Index of 70–100					Speed - m/min (ft/min)		Starting Conditions		⊕
Material Group	Grade	250 (800)	500 (1600)	750 (2400)	1000 (3200)	m/min		ft/min	
N4	HTSU10	⊕				260		850	

Speeds and Feeds



Grades

Nylon, Plastics, Rubbers, Phenolics, Resins, Fiberglass

Speed - m/min (ft/min) **Starting Conditions** ⊕

Material Group	Grade	250 (800)	500 (1600)	750 (2400)	1000 (3200)	m/min	ft/min
N5	HTSU10	⊕				105	345

Tin Alloys, Cast: ASTM 823, Alloys 1, 2, 3, 11

Speed - m/min (ft/min) **Starting Conditions** ⊕

Material Group	Grade	250 (800)	500 (1600)	750 (2400)	1000 (3200)	m/min	ft/min
N6	HTSU10	⊕				180	590

Iron-Based, Heat-Resistant Alloys (135–320 HB) (≤34 HRC)

Speed - m/min (ft/min) **Starting Conditions** ⊕

Material Group	Grade	15 (50)	45 (150)	75 (250)	105 (350)	140 (450)	170 (550)	200 (650)	230 (750)	290 (950)	310 (1050)	m/min	ft/min
S1	HTM15		⊕									55	180
	HTM25		⊕									40	130
	HTS10		⊕									55	180
	HTS25		⊕									40	130
	HTS35		⊕									40	130
	HTSU10		⊕									30	100
	HTH05			⊕								100	325

Cobalt-Based, Heat-Resistant Alloys (150–425 HB) (≤45 HRC)

Speed - m/min (ft/min) **Starting Conditions** ⊕

Material Group	Grade	15 (50)	45 (150)	75 (250)	105 (350)	140 (450)	170 (550)	200 (650)	230 (750)	290 (950)	310 (1050)	m/min	ft/min
S2	HTM15		⊕									60	195
	HTM25		⊕									30	100
	HTS10		⊕									60	195
	HTS25		⊕									30	100
	HTS35		⊕									30	100
	HTSU10		⊕									35	115
	HTH05			⊕								100	325

Nickel-Based, Heat-Resistant Alloys (140–475 HB) (≤48 HRC)

Speed - m/min (ft/min) **Starting Conditions** ⊕

Material Group	Grade	15 (50)	45 (150)	75 (250)	105 (350)	140 (450)	170 (550)	200 (650)	230 (750)	290 (950)	310 (1050)	m/min	ft/min
S3	HTM15			⊕								70	230
	HTM25		⊕									40	130
	HTS10			⊕								70	230
	HTS25		⊕									40	130
	HTS35		⊕									40	130
	HTSU10		⊕									40	130
	HTH05				⊕							100	325

Titanium and Titanium Alloys (110–450 HB) (≤48 HRC)

Speed - m/min (ft/min) **Starting Conditions** ⊕

Material Group	Grade	15 (50)	45 (150)	75 (250)	105 (350)	140 (450)	170 (550)	200 (650)	230 (750)	290 (950)	310 (1050)	m/min	ft/min
S4	HTM15			⊕								70	230
	HTM25		⊕									55	180
	HTS35		⊕									55	180
	HTSU10		⊕									45	150
	HTH05				⊕							100	325

Hardened Steel (>55 HRC)

Speed - m/min (ft/min) **Starting Conditions** ⊕

Material Group	Grade	15 (50)	45 (150)	75 (250)	105 (350)	140 (450)	170 (550)	200 (650)	230 (750)	290 (950)	310 (1050)	m/min	ft/min
H1	HTH05				⊕							100	325

Hardened Steel (≤60 HRC)

Speed - m/min (ft/min) **Starting Conditions** ⊕

Material Group	Grade	15 (50)	45 (150)	75 (250)	105 (350)	140 (450)	170 (550)	200 (650)	230 (750)	290 (950)	310 (1050)	m/min	ft/min
H2	HTH05				⊕							100	325

Chilled Cast Iron

Speed - m/min (ft/min) **Starting Conditions** ⊕

Material Group	Grade	15 (50)	45 (150)	75 (250)	105 (350)	140 (450)	170 (550)	200 (650)	230 (750)	290 (950)	310 (1050)	m/min	ft/min
H4	HTH05				⊕							100	325



Speeds and Feeds



Feed Rate, Per Revolution (in/min)
$v_f = f_n \cdot n$

Feed Rate, Per Tooth (in/min)
$v_f = f_z \cdot n \cdot Z$

Feed Per Revolution (in/rev)
$f_n = \frac{v_f}{n}$

Feed Per Tooth (in)
$f_z = \frac{v_f}{n \cdot Z}$

Cutting Speed (ft/min)
$v_c = \frac{\pi \cdot D_{tool} \cdot n}{12}$

Spindle Speed (rev/min)
$n = \frac{v_c \cdot 12}{\pi \cdot D_{tool}}$

Material Removal Rate (in ³ /min)
$MMR = a_p \cdot a_e \cdot v_f$

Inch

Symbol	Definition	Unit
V_f	Feed rate	in/min
f_n	Feed per revolution	in/rev
f_z	Feed per tooth	in
V_c	Cutting speed	ft/min (SFM)
n	Spindle speed	rev/min (RPM)
D_{tool}	Tool cutting diameter	in
MMR	Material removal rate	(in ³ /min)
a_e	Radial depth of cut	in
a_p	Axial depth of cut	in
Z	Number of teeth/flutes	

Speeds and Feeds



**Feed Rate, Per Revolution
(mm/min)**

$$v_f = f_n \cdot n$$

**Feed Rate, Per Tooth
(mm/min)**

$$v_f = f_z \cdot n \cdot Z$$

**Feed Per Revolution
(mm/rev)**

$$f_n = \frac{v_f}{n}$$

**Feed Per Tooth
(mm)**

$$f_z = \frac{v_f}{n \cdot Z}$$

**Cutting Speed
(m/min)**

$$v_c = \frac{\pi \cdot D_{tool} \cdot n}{1000}$$

**Spindle Speed
(rev/min)**

$$n = \frac{v_c \cdot 1000}{\pi \cdot D_{tool}}$$

**Material Removal Rate
(cm³/min)**

$$MMR = \frac{a_p \cdot a_e \cdot v_f}{1000}$$

Metric

Symbol	Definition	Unit
V_f	Feed rate	mm/min
f_n	Feed per revolution	mm/rev
f_z	Feed per tooth	mm
v_c	Cutting speed	m/min (SMM)
n	Spindle speed	rev/min (RPM)
D_{tool}	Tool cutting diameter	mm
MMR	Material removal rate	(cm³/min)
a_e	Radial depth of cut	mm
a_p	Axial depth of cut	mm
Z	Number of teeth/flutes	